



Our "high strength members" solution which consists in applying high adhesion and waterproof HDPE coating to a zinc-coated steel wires to meet your highest strength cable requirements. The maximum steel wire diameter we may coat is 5,0mm and the maximum final coated outer diameter is 15,0mm. By using our HDPE Coated Steel Wires you release your own extrusion capacity and then save time and money. => monthly capacity 3 000km



MATERIAL SAFETY DATA SHEET



ISO 9001 CERTIFICATE

HDPE Coated Steel Wires Characteristics

| Steel Wire Size | Coating Diameter | Coating Thickness | Sheath Thickness Deviation |
|-----------------|------------------|-------------------|----------------------------|
| 2.0mm | 2.7±0.05mm | 0.35mm | Min. 80% |
| 2.3mm | 3.5±0.05mm | 0.60mm | Min. 80% |
| 2.6mm | 5.0±0.10mm | 1.90mm | Min. 80% |
| 2.6mm | 6.4±0.15mm | 1.20mm | Min. 80% |

We can support the production of different sizes according to customer requirements.

Steel Wires Characteristics

| ITEM | UNIT | SPECIFICATION | TEST METHOD |
|------------------|--------|---------------|-------------|
| Tensile Strength | kg/mm² | Min. 100 | ASTM D 3916 |



| ITEM | UNIT | SPECIFICATION | TEST METHOD |
|------------------------|-------|---------------|-------------|
| Elongation at Break | % | Min. 2.5 | ASTM D 3916 |
| Twist | Times | Min. 1000 | - |
| Amount of Zinc Coating | g/m² | Min. 150 | - |